

№п/п	Влажность среды φ, %	Температура t, °C
бук, ясень 50 мм; дуб 32 мм		
1	0	77
2	34	77
3	74	61
4	85	57
5	100	57
бук, ясень 32 мм		
1	0	83
2	32	83
3	71	67
4	82	63
5	100	63
дуб 50 мм		
1	0	70
2	33	70
3	76	55
4	84	52
5	100	52
сосна 50 мм		
1	0	94
2	32	94
3	70	75
4	83	71
5	100	71
сосна 32 мм		
1	0	100
2	30	100
3	64	80
4	80	75
5	100	75

